Product Data Sheet

ONEGEL



Products may differ in size, colour and appearance to those shown. If you require further information or customisation, please contact us directly.

Dielectric strength	18 kV/mm
Pot life at 23°C min	12
Curing time at 23°C min	20
Volume	300 ml
Type	ONEGEL
UK-Number	ONEGEL
WISKA-Order no.	10108963
Packing unit	1
ETIM-Classification	EC001168

Remarks:

Colour: Transparent Clear
Mixing Ratio: 1

Describtion:

ONEGEL IP 68 junction box filler, 300ml Cartidge, no mixing required (mono-component silicone gel), ready for immediate use.

Additional Info:

Ready to use, re-enterable, no mixing, excellent electrical insulation, good mechanical strenght, non toxic, no expiry date.

18.03.2026

Your Contact:
WISKA UK Ltd.
Unit 7, Hurling Way · St. Columb Major Business Park · TR9 6SX, St. Columb Major, Cornwall · Great Britain
☎ +44-12-08816062 · 🖷 +44-12-08816708
info@wiska.co.uk · www.wiska.co.uk

Other technical data on request / subject to change without notice